

Developing times SILVERMAX 21

Developing times for Silvermax in different developers.

Agitation: Agfa Agitation (the first minute continuously then every half minute 1 tilt)

SILVERMAX 21 can be reversal processed in Agfa SCALA reversal process.

Expose to 100 ASA / 21° DIN

For other developers start with the indicated time for Agfa APX 100 (old) and decrease in steps of 10%

ADONAL/Rodinal	20 °C	1+25	8	0,65
ADONAL/Rodinal	20 °C	1+50	12	0,65
ADONAL/Rodinal	20 °C	1+25	Min.	0,65
ATOMAL	20 °C	Stamm	8-10	0,65
Kodak D76 / Ilford ID 11	20 °C	Stamm	9	0,65
Kodak HC 110	20 °C		7	0,65
Kodak XTOL	20 °C	Stamm	7	0,65
Paterson FX 39	20 °C		8	0,65
SILVERMAX Entwickler	20 °C	1+29	11	0,65